

STEARIC ACID

Rubber Grade - SA 101



Product Data Sheet

TEST	SPECIFICATION		
	Method AOCS	Min.	Max.
Colour Lov, 5.25" Cell R/Y	Cc 13j-97	-	2.0 / 15.0
Acid value (mgKOH/g)	Te 1a-64	200	218
Saponification value (mgKOH/g)	Tl 1a-64	202	220
Iodine value (gl ₂ /100g)	Tg 1a-64	-	10
Titer (°C)	Tr 1a-64	50	-

Package: 25 kg PP or PE bags