

TITANIUM DIOXIDE R-298



Product Data Sheet

TEST	SPECIFICATION
<i>TiO₂ content, %</i>	≥93.0
<i>Rutile content, %</i>	≥98.0
<i>Volatile at 105 °C</i>	≤0.8
<i>Brightness, %</i>	≥95.0
<i>Residue on sieve (45 um)</i>	≤0.02
<i>Oil absorption, g/100g</i>	≤20.0
<i>Dispersibility</i>	≥6.50
<i>PH Value</i>	6.0-9.0

APPLICATION:

- Architectural exterior coatings
- Exterior industrial finishes
- Powder coatings
- Container coatings
- Coil coatings
- Ink

PACKAGE: 25kg paper-plastic compound bags, 20MT/FCL

STORAGE: Stored in good ventilation, clean & dry place.